

IN THE CLAIMS

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) An abrasion-resistant and noise-suppressing tape for bandaging cable harnesses, comprising a backing with a first outer layer A having a first side, wherein the first side of the first outer layer A is connected to a separate ~~second~~ layer C over an entire area of the first side of the first outer layer A, wherein the layer C is firmly connected on an open side to a separate second outer layer B over an entire area of a first side of the second outer layer B, wherein
the first outer layer A ~~is being~~ composed of a velour, scrim, woven fabric or formed-loop knit,
the second outer layer B is composed of a velour, scrim, woven fabric or formed-loop knit, and
the layer C being composed of a textile having an open but stable three-dimensional structure.
2. (Canceled)
3. (Previously Presented) The tape according to claim 1, which exhibits an abrasion resistance of the backing (measured in accordance with ISO 6722, section 9.3, "Scrape abrasion resistance") of at least 150% of the sum of the abrasion resistances of the individual plies.
4. (Previously Presented) The tape according to claim 1, wherein the layer C is a spacer knit, a loop product, a three-dimensional nonwoven structure or a warp knit and/or the layer C has a basis weight of 100 to 500 g/m².
5. (Previously Presented) The tape according to claim 1, wherein the layer C has a density of 100 to 600 g/dm³ and/or a thickness of 0.2 to 3 mm.

6. (Currently Amended) The tape according to claim 12, further comprising a mechanical bond formation joining, without adhesive, the separate layers A, B and C to form an assembly.
7. (Currently Amended) The tape according to claim 12, wherein the layers A, B, and C comprise wear-resistant polymers.
8. (Currently Amended) The tape according to claim 1, wherein the backing is coated at least on one side with a self-adhesive layer, wherein the layer C has a thickness defined between a first side and a second side opposite to the first side, wherein the entire thickness of layer C is located between the first side of the first outer layer A and the self-adhesive layer.
9. (Withdrawn) A method of wrapping an elongate product comprising guiding the tape as claimed in claim 1 in a helical spiral around the elongate product.
10. (Withdrawn) A method of wrapping an elongate product comprising sheathing the elongate product with the tape as claimed in claim 1 in its axial direction.
11. (Withdrawn) Elongate product wrapped with a tape as claimed in claim 1.
12. (Withdrawn) A vehicle comprising the elongate product as claimed in claim 11.
13. (Currently Amended) The tape according to claim 12, further comprising a first laminating adhesive joining the separate layers A, B and C and a second laminating adhesive joint the separate layers C and B to form an assembly.
14. (Previously Presented) The tape according to claim 8, wherein the self-adhesive layer is made of a rubber or acrylate or silicone adhesive